



Fraunhofer

TESTED[®] DEVICE

Bosch Rexroth AG
Radial Compensation 45, GREY
Report No. BO 2112-1289

Statement of
Qualification

Single product
Outgassing Behavior
VOC/SVOC

Statement of Qualification · Single product

Customer	Bosch Rexroth AG Löwentorstrasse 74 91136 Stuttgart Germany
Component tested	
Category:	Materials
Subcategory:	Plastics
Product name:	RADIAL COMPENSATION 45, GREY, 3842551030 (manufacturing date: 11/2021; color: RAL7004; drawing number: 3842551030; supplier number: 36588)
Emission chamber measurements with purge-and-trap thermodesorption method and gas chromatography combined with mass spectrometry (TD-GC/MS)	
Standards/Guidelines:	ISO 14644-8, -15; ISO 16000-6, -9, -11, -25; VDI 2083 Part 17 The norms stated generally refer to the version valid at the time of the tests.
Testing equipment:	<ul style="list-style-type: none">Measuring station:PerkinElmer Clarus 600, Clarus 600T, ATD 650Sampling chamber:.....Markes International µCTE
Sample storage:	<ul style="list-style-type: none">Pre-conditioning:<ul style="list-style-type: none">Cleanroom Air Cleanliness Class (according to ISO 14644-1):ISO 1Airflow velocity:0.45 m/sAirflow type:..... vertical laminar flowTemperature:22 °C ± 0.5 °CRelative humidity: 45 % ± 5 %Purified air: VOC-filtered
Test procedure parameters:	<ul style="list-style-type: none">Retention range (VOC): C6 to C16Outgassing test temperatures: 23 °C and 90 °C

Test result / Classification

The outgassing behavior of RADIAL COMPENSATION 45, GREY, 3842551030 at the stated temperatures was investigated according to VDI 2083 Part 17 and ISO 14644-15. Based on the outgassing rates determined for the specific surfaces, the following material classification was made for the corresponding Contaminant Category:

Contaminant Category (x)	SER _a ¹⁾ 23 °C [g/m²s]	SER _a ¹⁾ 90 °C [g/m²s]	ISO-ACC _m Class (x) based on 23 °C
VOC	4.4 x 10 ⁻⁹	3.2 x 10 ⁻⁹	-8.4
SVOC	1.4 x 10 ⁻⁹	< 1.7 x 10 ⁻⁹	-8.9
Amines	< 2.8 x 10 ⁻¹⁰	< 1.7 x 10 ⁻⁹	--
Organophosphates	< 2.8 x 10 ⁻¹⁰	< 1.7 x 10 ⁻⁹	--
Siloxanes	< 2.8 x 10 ⁻¹⁰	< 1.7 x 10 ⁻⁹	--
Phthalates	< 2.8 x 10 ⁻¹⁰	< 1.7 x 10 ⁻⁹	--

¹⁾SER_a: Area-specific emission rate


The measuring devices used for the qualification tests are calibrated at regular intervals; their results can be traced back to national and international standards. In cases where no national standards exist, the test procedure implemented complies with the technical regulations and norms applicable at the time of the test. The relevant documentation can be viewed on request at any time.

Detailed information and parameters of the test environment can be found in the Fraunhofer IPA test report.

Fraunhofer Institute for Manufacturing Engineering and Automation IPA

Department of Ultraclean Technology and Micromanufacturing

Nobelstrasse 12
70569 Stuttgart
Germany

BO 2112-1289	Stuttgart, April 13, 2022
Report No. first document	Place, date of first document issued
--	--
Report No. current document	Place, current date
on behalf of	
Dr.-Ing. Frank Bürger, Project Manager Fraunhofer IPA	



This document only applies to the named product in its original state and is valid for a period of 5 years from the date the first document was issued. The document can be verified under www.tested-device.com.